
	<p><b>EVALUATE.ENGINEER.EXECUTE</b>  <i>Experts in custom wear solutions for over 40 years</i></p>	
	<p><b>CLS-222 RTV Silicone</b></p>	

**CLS-222** is a single component silicone adhesive sealant which cures to a tough, rubbery solid at room temperature on exposure to water vapor in the air (acetoxo cure).

**CLS-222** adheres to clean substrates such as ceramic, metal, glass, most woods, painted surfaces and can be applied overhead without sagging. **CLS-222** is 100% silicone, retains permanent flexibility and has excellent weatherability.

**CLS-222** is ideal for use on:

• Applying Ceramic Tiles	• Gaskets in Refrigeration Units
• Anti-abrasion Coating	• Applying Nameplates
• Sealing Windows	• Brick Corners
• Sealing Marine Cabins	• Gaskets in Heating Units
• Caulking Joints	• Formed in place Gaskets

**CLS-222** is available in (10.3) oz. caulk tubes and (1) gallon containers.

<b>Application Instructions</b>
---------------------------------

1. Prepare surface by sandblasting or grinding to eliminate surface scale, rust and loose materials. Surfaces should be free of paints, sealants, oils or other coatings.
2. Do not apply if frost is present and not for use on wet or oily surfaces
3. If using tubes, cut tip to desired bead size and dispense with caulking gun. Apply sealant at 45° angle by pushing sealant ahead of nozzle. If using (1) gallon pails dispense using a putty knife.
4. Work material with notched putty knife or similar tool
5. Allow 30 minutes to touch; 24 hours for full cure and strength.
6. Consult SDS for full listing of PPE requirements

<b>Physical Properties</b>	
Color	Clear
Specific Gravity	1.04
Durometer, Shore A	26
Extrusion Rate	330 g/min
Skin Over / Tack Over Time	10 - 20 minutes
Cure Time	24 Hours
Tensile Strength	363 psi
Elongation	640%

<b>Physical Properties</b>	
Peel Strength: Aluminum (Steel)	18 (20) piw
Dielectric Strength kv/mm (v/mil)	20 (500)
Dielectric Constant @ HZ	2.9 @ 60
Service Temperature	-62° F to 400° F
Intermittent Temperature	425° F
Shelf Life (factory sealed containers)	12 Months
Conforms to Specifications; FDA CFR.177.2600, USDA, NSF51, MIL-A-46106, ASTM C920, TT-S-111543A, TT-S-00230C (COM-NBS), UL File No. E163852 (E40195) (Type 37132, Amend 2, Type 1)	

**Product Warranty:** C. L. Smith Industrial Company warrants its products to be free of manufacturing defects and that, at the time and place of shipment, our material will meet current published physical properties when applied within C.L. Smith Industrial's directions and tested in accordance with ASTM and C.L. Smith Industrial standards. C.L. Smith Industrial Company's liability is limited to replacement of material found to be defective. As C.L. Smith Industrial has no control over the use to which others may put its products, it is recommended that the products be tested to determine if suitable for a specific application and/or our information is valid in a particular circumstance. Responsibility remains with the architect, engineer, contractor and owner for the design, application and proper installation of each product. Nothing contained herein shall be construed to be a recommendation to use or as a license to operate under or to infringe any existing patents. Data sheets are subject to change without notice.